



Your Quality Source for Electrical Wire

U.L. AWM Style 3289

AWG	COND. STRANDING	NOM. INSUL. THICK. (IN)	NOM. O.D. (IN)	APPROX LBS/MFT
26	7/34	.031	0.0810	3.80
24	7/32	.031	0.0860	4.60
22	7/30	.031	0.0920	5.80
20	7/28	.031	0.1020	7.30
20	10/30	.031	0.1010	7.20
18	16/30	.031	0.1090	9.30
16	26/30	.031	0.1220	13.60
14	41/30	.031	0.1370	19.20
12	65/30	.031	0.1560	28.00
10	65/30	.031	0.1810	43.00
10	105/30	.031	0.1820	43.00
8	84/27	.047	0.2500	72.00
8	133/29	.047	0.2630	74.00
6	84/25	.065	0.3300	115.00
6	133/27	.065	0.3390	121.00
4	133/25	.065	0.3950	180.00
2	259/26	.065	0.4660	262.00
2	665/30	.065	0.4530	267.00
1	817/30	.085	0.5500	347.00
1/0	259/24	.085	0.5940	435.00
1/0	1045/30	.085	0.5830	425.00
2/0	259/23	.085	0.6470	540.00
2/0	1330/30	.085	0.6450	530.00
3/0	259/22	.085	0.7100	660.00
3/0	1672/30	.085	0.7050	651.00
4/0	259/21	.085	0.7710	825.00
4/0	2109/30	.085	0.7600	811.00

UL 3289

Irradiated Cross-linked Polyethylene

Electronic Hook Up Wire

UL Recognized & CSA Certified

150°C, 600V

UL 3289 Description:

Conductor: UL 3289 possesses a soft annealed, solid or stranded, tinned copper conductor

Insulation: Irradiation Cross-Linked Polyethylene Insulation

Available Options: VW-1 Compound available. Prefused material available upon request for UL 3289

UL 3289 Applications:

UL 3289 Hook Up Wire may be used for internal wiring of appliances, computers, test equipment, business machines and other office and control equipment.

